

Espuma de PVC 100



Densidad kg/m ³	ASTM D1622	kg/m ³	nominal	100
Resistencia a la compresión	ASTM D1621-10	MPa	average min-ave min-min	1,93 1,72 1,47
Modulo de compresión	ASTM D1621-10	MPa	average min-ave min-min	90 76 64
Resistencia a la rotura	ASTM D1623	MPa	average min-ave min-min	3,08 2,31 2,06
Modulo de rotura	ASTM D1623	MPa	average min-ave min-min	169 138 123
Resistencia al corte	ASTM C273	MPa	average min-ave min-min	1,49 1,43 1,25
Modulo de corte	ASTM C273	MPa	average min-ave min-min	37 33 29
Alargamiento de corte a la rotura	ASTM C273	%	average	25
Medidas estandar		mm		950 2050 68